

PRODUCT DATASHEET

Insulation Retaining Washer

PRODUCT DETAILS

Designed For:

Evolution Insulation Washers are used in conjunction with various screw types to secure rigid PIR (Polyisocyanurate) and PUR (Polyurethane) insulation panels/ boards to various substrates (commonly timber, steel and masonry).

Technical Information:

All washers have a recessed mounting point for the screw heads: this ensures that the screw head is below the surface of the washer and aids in reducing cold-bridging

Both Polycaprolactam (commonly referred to as "Nylon 6") and Polypropylene are polymers which are stable under exposure to low levels of ionising radiation (Ultraviolet, X-Ray, etc).

They are also stable under exposure to certain aggressive chemicals.

Products have radial holes and other head surface features to allow render to "key" (mechanically adhere) to the washers.

Image is a real photograph of the actual product described
Illustrated image is representative of the full range.
Please refer to the corresponding drawing file for 1:1 scale replication per SKU

General Physical Characteristics

SKU	Nominal Head Diameter (mm)	Nominal Body Fixing Length (mm)	Extension to Fixing Length (mm)	Material	Colour	Encapsulated Head
RW5	46.0	5.0	2.0	Polycaprolactam	Black	No
RW18	46.0	18.0	13.0	Polycaprolactam	Black	No
RW35	50.0	35.0	20.0	Polycaprolactam	Black	No
RW65	50.0	65.0	50.0	Polycaprolactam	Red	No
RW105	50.0	105.0	80.0	Polycaprolactam	Red	No
RW165	50.0	165.0	140.0	Polycaprolactam	Red	No
EVPPW50	50.0	N/A	N/A	Polypropylene	Black	No
ECW60	60.0	12.0	10.0	Polycaprolactam	White	Yes
ECW70	70.0	12.0	10.0	Polycaprolactam	White	Yes

Polycaprolactam Chemical and Physical Properties

Parameter	Data
Chemical Formula	(C6H11NO)n
Density	1.084 g/ml
Melting Point	493 K
Autoignition Temperature	707 K
Tensile Strength	10.5 MPa

Polypropylene Chemical and Physical Properties

Parameter	Data
Chemical Formula	(C3H6)n
Density	0.855 g/ml
Melting Point	403 K
Autoignition Temperature	533 K
Tensile Strength	40 MPa

NOTE: The results expressed in this document are determined from empirical testing. Specifiers, end-users and other third parties should make their own decision(s) on what safety factors to use relevant to their design(s)/ application(s). This document is provided, strictly: without prejudice, without recourse, without liability, non-assumpsit, no assured value, errors and omissions excepted, subject to change without notice and all rights reserved.
©Evolution Fasteners UK Ltd, 2021.