Technical Datasheet

DuPont[™] AirGuard[®] Tape

Product Description & Application

A high performance, flexible and universal Air & Vapour Control Layer Tape (AVCL-Tape). Suitable for airtight sealing of membrane laps, joints, junctions, windows and doors and sealing around penetrations such as pipework, wiring and structural elements. Good adhesion to various smooth and slightly rough substrates; timber, masonry, aluminium, steelwork, UPVC, PE and PP membranes. Recommended for internal use with AirGuard® AVCL's.

Product composition	
Carrier:	Flexible PE film, white
Adhesive:	Acrylic
Release liner:	Siliconized paper

Specifications

PROPERTY	STANDARD	VALUE
Stylename		1310V
Colour		White
Thickness	DIN EN 1942	арргох. 270 µm
Basis weight		approx. 375 g/m²
Temperature range		-40 °C to 70 °C
Installation temperature		> -5°C (*)
Airtightness (**)	DIN 4108-2 DIN 18542	airtight meets BG R
Tensile strength	DIN EN 14410	approx. 25 N/cm
Elongation at break	DIN EN 14410	арргох. 450 %
Adhesion to steel	DIN EN 1939	approx. 12 N/cm
GEV-EMICODE	EC1 Plus	
(*): depending on the substrate this may b	be slightly different. A self sticky testing ma	y be necessary before starting the installation.
(**): Massurad at a prossure difference of	600Pa Tested on an aluminum surface	

(**): Measured at a pressure difference of 600Pa. Tested on an aluminum surface.

Use and Care recommendations

- Highly flexible, hand-tearable reinforced carrier
- Good temperature resistance
- High water vapour resistance
- Acrylic adhesive with excellent ageing resistance
- Solvent free adhesive
- Up to 4 months resistant to UV (when used for outdoor applications)
- Not sensitive to contact with water
- In cases where adhesion is not effective due to the surface of the building material being very porous, non-stable, chalky or sandy the DuPont[™] Tyvek[®] Primer is recommended beforehand
- The surface should be free from dirt, moisture, ice, grease and other materials which potentially reduce adhesion strength

Storage recommendations:

• Store rolls in original packaging lying flat in a dry and clean place at temperatures between +5°C & 35°C and away from direct sunlight

DuPont de Nemours (Luxembourg) S.à r.l. Rue General Patton, L - 2984 Luxembourg Tel.: +352 3666 5885 tyvek.info@lux.dupont.com

www.building.dupont.co.uk

This information corresponds to our current knowledge on the subject. It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for any application other than the application as specified herein. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liabilities in cornnection with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature. Date: April 14, 2020

