DuPont™ Tyvek® Metallised Tape

Technical Datasheet

Product Description & Application

Single-sided metallised DuPont[™] Tyvek® (HD-PE) with high coat weight water based modified acrylic adhesive and a paper interliner. DuPont[™] Tyvek® Metallised Tape is suitable for sealing membrane laps and penetrations and for damage repair for all DuPont[™] Tyvek®Underlays and Vapour Control Layers.

Specifications

PROPERTY	VALUE
Stylename	2060M
Colour	Metallised
Thickness	300 µm
Basis weight	210 g/m²
Temperature range	-40 °C to 100 °C
Tensile strength	300 N/5cm
Elongation at break	15 %
Peel adhesion	25 N/25mm

Use and Care Recommendations

- Product is designed for the building industry. Tyvek® Metallised Tape has a high immediate tack and excellent adhesion onto Tyvek® and a wide range of plastic materials (e.g. non-woven, plastic film, wood, metal,....).
- Users must check that the Tyvek® Metallised Tape is suitable for their specific application (adhesion, chemical compatibility, staining,....).
- The resistance to ageing, water, humidity, environmental cycling and chemicals is excellent.
- The recommended application temperature is > 0 °C. The application should be done on a dry and clean surface (no dust, no grease, no solvent,...).
- Storage conditions: store rolls in their initial packaging, flat, in a clean and dry place. Storage temperature between +10 °C & 30 °C whitout direct exposure to UV-light.

DuPont de Nemours (Luxembourg)S.à r.l. L - 2984 Luxembourg E-mail: tyvekinfo@dupont.com Tel. +352 3666 5885

www.building.dupont.co.uk

Date: January 06, 2020

This information corresponds to our current knowledge on the subject. It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for any application other than the application as specified herein. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liabilities in connection with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature.

