

General Purpose PVA

Multi Surface Adhesive, Primer, Sealer and Admixture

- Bonds a wide variety of building materials including wood, plaster, concrete and ceramics

Colour	Product Code	Pack Size	Box Qty
White	FBGPPVA5	5KG	4
	FBGPPVA25	25KG	1



Bonding Agents

Product Description

FEB GENERAL PURPOSE PVA is an economical quick drying adhesive, sealer and bonding agent and cement admixture which has many applications.

Typical Uses

- FEB GENERAL PURPOSE PVA will bond most common building materials - except PVC, rubber and polythene - to themselves and to each other.
- As a bonding agent for cement screeds and render, plaster and concrete.
- As an admixture for mortar and an admixture in cements/sand and granolithic screeds.
- As a sealing coat - FEB GENERAL PURPOSE PVA minimises dusting.

Features & Benefits

- Numerous applications in the building industry from one product.
- Economical and simple to use/exceptional adhesive properties/quick drying.

Instructions for Use

As an adhesive

On smooth, flat surfaces, coat both faces with FEB GENERAL PURPOSE PVA diluted with an equal volume of water. Allow to become tacky then press together. When bonding smooth wood to wood, apply a thin coat of neat FEB GENERAL PURPOSE PVA to one face only and press together firmly. On large areas, such as laminated plastic, clamping or weights may be required until the bond is set (usually after 24 hours, depending upon surface porosity).

Dilution Rate

As a sealer coat: 1 part FEB GENERAL PURPOSE PVA to 4 parts water. As a bonding coat: Use neat and apply after application of a 1:4 sealer coat.

Note: Allow the sealer coat to dry prior to the application of the bonding coat. On totally non-absorbent surfaces, such as polished grano, etc. the sealer coat may be omitted.

If surfaces to be bonded are very porous, first prime with 1 part FEB GENERAL PURPOSE PVA diluted with 3 parts clean water and allow to dry.

As a bonding agent for cement screed and renderings, plaster etc: The background must be sound. Remove all flaking and cracking plaster etc. The surface must be clean, and free from oil and grease. Seal the surface using FEB GENERAL PURPOSE PVA (1:4 dilution). Allow this to dry, then apply a neat bonding coat of FEB GENERAL PURPOSE PVA. Screed, plaster or render on the tacky bonding coat using established sound practice.

Bonding New Concrete to old: Apply a sealing coat of FEB GENERAL PURPOSE PVA diluted with 4 parts of clean water and allow to dry. Apply a bonding coat of neat FEB GENERAL PURPOSE PVA and lay the new concrete while this coat is still tacky. To ensure maximum bond strength, add approx 2 litre of FEB GENERAL PURPOSE PVA per 50Kg bag of cement.

As a surface sealing coat: Apply 2 coats of FEB GENERAL PURPOSE PVA diluted at the rate of 1 part FEB GENERAL PURPOSE PVA to 4 parts water and a final coat diluted 1 part FEB GENERAL PURPOSE PVA to 3 parts water. Allow each coat to dry before proceeding. On less porous floors, the first coat may be omitted.

As an admixture in cement/sand and granolithic screeds: The use of FEB GENERAL PURPOSE PVA in the mix allows thin, jointless floor screeds (9-18mm thick) to be laid without the need for setting out bays, new levels, etc. For domestic use and other areas subject to light traffic, use

3 parts sand, 1 part cement and 10 litres of FEB GENERAL PURPOSE PVA per 50Kg of cement. For an industrial floor finish or where there is heavy traffic, use 1 part sand, 1 part cement and 2 parts 6 to 3mm granite (no dust) plus 10 to 15 litres of FEB GENERAL PURPOSE PVA per 50Kg of cement.

Follow the instructions given above for preparation, sealing and bonding. Lay the screed on to the tacky bonding coat, tamping well to ensure maximum contact with the floor beneath. Trowel to smooth finish. Setting time is normally 36 hours to 48 hours. Allow 3 to 7 days before opening to traffic, depending upon the severity of the traffic (longer may be required in cold temps).

Coverage

As a primer/adhesive:

Neat 1 litre per 6-12 sq mtrs.
Diluted 1:4: 1 litre per 24-48 sq mtrs.
Diluted 1:3: 1 litre per 18-36 sq mtrs.

The above figures will vary according to the degree of porosity and texture of the surface to which FEB GENERAL PURPOSE PVA is applied.

As an admixture: FEB GENERAL PURPOSE PVA is added at the rate of 10 to 15 litres per 50Kg of cement used i.e. approx. 100 to 150 litres per cubic metre of mortar.

Storage

Store at ambient temperatures - protect from frost.

Shelf Life

Up to 12 months if stored in unopened containers according to manufacturer's instructions.

Performance Data

Viscosity @ 23°C Brookfield RVT 5/20	120-200 poise
pH	4.5-5.5
Minimum Film Forming Temperature (°C)	Approx 2
High Temperature Stability (1 week @ 50°C)	Stable
Specific Gravity @ 20°C	1.03
Cleaning	Clean all equipment in water immediately after use.

General Purpose PVA